

Motive Battery-Deep Cycle Type-TNE Series

TNE12-150 (12V 150Ah)


GENERAL FEATURES

- Oxygen recombination technology:Maintenance Free VRLA Battery, no need to add water or acid
- The patent grid alloy:less gassing, low self-discharge, excellent corrosion resistence performance
- Special paste formula: addictives are added to improve deep discharge,long cycle life
- High quality AGM separator: extend cycle life and prevent micro short circuit
- ◆ The patent Nano silica gel electrolytes, extend cycle life and improve the deep discharge performance
- ABS container: increase the strength of battery (Flame-retardant ABSUL94-V0 is optional)

Dimension

Unit:mm

407±2mm	/	16.02inch
171±2mm	/	6.73inch
240±2mm	/	9.45inch
240±2mm	/	9.45inch
	171±2mm 240±2mm	407±2mm / 171±2mm / 240±2mm / 240±2mm /








Application

- Electric tools or toys
- Electric Bicycle/Tricycle
- ٠ Golf trolleys and golf cart
- Patrol car ٠
- ٠ Electric Sight-seeing Tour Bus
- ٠ Sweeper
- Wheelchairs ٠

Terminal

- Lawn mowers
- Illumination light




Weight	

41kg

90.39lbs

This document is subject to change without prior notification

Tianneng Battery Group Co., Ltd.	Changxing Tianying Import & Export Co., Ltd.	www.tiannenggroup.com	Version:	V1.0	Release Date:	2016/7/1
@2016 All right reserved by Tianneng Group: Trademarks and logos are the property of Tianneng Group and its affiliates			No 18th Baogiao Road Hua	i Industrial Zon	e of Changxing County. Zh	eijang China



Energy Storage Battery



Reserve Battery


Specificaion


Motorcycle Battery


TNE12-150

opeointealer	•	
Nominal Volta	ge	12V
Rated Capacity (25°C)	C20(1.80V/cell)	150Ah
	C10(1.80V/cell)	136Ah
	C5(1.75V/cell)	128Ah
	C3(1.70V/cell)	120Ah
	C2(1.70V/cell)	112Ah
Container Material		ABS (Flame-retardant ABSUL94-V0 is optional)
Operating Temperature Range	Discharge	-20 ~ +50°C
	Charge	0 ~ +40°C
	Storage	-15 ~ +40°C
	40°C / 104°F	106%
Capacity Effected by Temperature	25°C / 77°F	100%
	0°C / 32°F	86%
	-10°C / 14°F	65%
Charge Method		Please refer to the "Charge Characteristics (25°C) " below
Monthly Self Discharge		<3%, TNE series stored at 25 $^\circ\!\!C$ require a supplementary charge every six months, the charging interval would shrink when the ambient temperature went higher

Performance Curve









Tianneng Battery Group Co., Ltd.	Changxing Tianying Import & Export Co., Ltd.	www.tiannenggroup.com	Version:	V1.0	Release Date:	2016/7/1
@2016 All right reserved by Tianneng Gr	oup: Trademarks and logos are the property of Tianneng Group	and its affiliates	No.18th. Baogiao Road. Huaxi	i Industrial Zone of C	Changxing County, Zhe	eiiang, China